

Dawnprene TPE 6502-NA

TPE

30%gf PA6

TPE

Features:

It is a natural color thermoplastic elastomer (TPE) material. This material combines good physical properties, chemical resistance and elasticity, designed for bonding 30%gf PA6 applications. This grade of TPE can be processed on conventional thermoplastics equipment for injection. It is completely recyclable.

	30%gf PA6		
RoHS	RoHS		
	2016-08-23		
	0.98	g/cm³	ASTM D792
2	65	A	ASTM D2240
2	7.4	MPa	ASTM D412
2	700	%	ASTM D412
23	30	KN/m	ASTM D624
23 0	30	%	ASTM D395
70	43	%	
0.01%			
Drying Instructions: Need drying the granules before make molding,excessive moisture will lead materials bad extrusion surface,mechanical performance reduction and bad surface appearance. Moisture content request below 0.01%,suggesting drying as follow process:			
Drying conditions		Dring temperature/	Dring time/h
first choice		80 90	2 3
other choice		100	1
110		105	
If drying temperature over than 110 ,it might cause materials blocking in barrel zone;if use moisture analysis meter,the temperture setting should be on 105 .			



--

Dawnprene TPE is incompatible with PVC materials, hence must clean the equipment before using.

Above testing data is tested by injection sample block, cutting by the sheet size is 110 85 2 .

4. Any reprocessing must follow the above instructions, and ensure no content impurity.

SHANDONG DAWN POLYMER CO.,LTD	
:	. 265703
Address:Zhenxing Road,Longgang Economic Zone,Longkou,Shandong, China. 265703	
()	0086-535-8868588;()0086-535-8833988
Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988	