

◇	◇
◇	◇

Properties	Test Method	Test Condition	Unit	Test Results
Physical				
Density		23	g/cm ³	0.96
Ash		800 1h	%	
Melt Flow Rate		275 ,2.16kg	g/10min	
Mechanical				
Tensile Strength		50mm/min	MPa	20
Tensile Strain @ break		50mm/min	%	368
FlexuralStrength		2mm/min	MPa	20
Flexural Modulus		2mm/min	MPa	792
Notched Charpy Impact Strength		23	KJ/m ²	6
Thermal				
Heat deflection temperature		0.45MPa		-

Product information

Note: The above injection details should be based on the shape of products, mold design and injection molding machine specifications and other conditions vary,the specific shall be adjusted.