

Dawnprene TPV 10-65A

RoHS	RoHS			
		2021/11/3		
		0.943	g/cm ³	ISO 1183-1 2019
		0.80-1.10	%	ISO 294 2018
		1.00-1.50	%	ISO 294 2018
	(Shore A,15 sec,23)	65	A	ISO 48-4 2018
	, 500mm/minute 23	2.04	MPa	ISO 37 2017
	, 500mm/minute 23	520	%	ISO 37 2017
100%	, 500mm/minute 23	6.1	MPa	ISO 37 2017
	500 mm/minute	38	KN/m	ISO 34-1 2015
	23 ,70hr,Type B	29	%	ISO 815 2014
	70 ,22hr,Type B	35	%	
		25	mm/min	GB/T 8410-2006
		-50		ISO 812 2017
		-12.5	%	
		-18.5	%	
		+2.5	A	ISO188 2011
		-4.0	%	
	(200 pphm,40 ,72h)		/	ISO1431-1 2012
		80~90	°C	/
		2~3	h	/
		160~205	°C	/
		170~185	°C	/
		170~185	°C	/
		50~70	°C	/

1. 110

3. Dawnprene TPV PVC

4. 120 x100 x2

5.

6

71.