

Dawnprene TPE 6302-PB

TPE

TPE

Features:
It is a natural, thermoplastic elastomer (TPE) material. This material combines good physical properties,chemical resisittance and elasticity, designed for injection applications.This grade of TPE can be processed on conventional thermoplastics equipment for injection.It is completely recyclable.

(GENERAL)			
(Application)	general injection		
RoHS Compliance	RoHS		
(Color)	Natural		
(Form)	Pellet		
(Processing Method)	injection		
(Revision Date)	2023-05-29		
Physical	Typical Value	Unit	Test Method
(Density)	1.03	g/cm³	ASTM D792
(Hardness)			
Shore Hardness(Shore A, 10 sec,2	65	A	ASTM D2240
- 2 Tensile strength-parallel flow direction 2	6.0	Mpa	ASTM D412
- 2 2	700	%	ASTM D412
100% - 2	1.8	Mpa	ASTM D412
300% - 2	3.0	Mpa	ASTM D412
- 2	40	KN/m	ASTM D624
0.1% Drying Instructions: Need drying the granules before make molding,excessive moisture will lead materials bad extrusion surface,mechanical performance reduction and bad surface appearance. Moisture content request below 0.1%,suggesting drying as follow process:			
Drying conditions	Drying temperature/	Drying time/h	
first choice	80 90	2 3	
other choice	100	1	
110 105			
If drying temperature over than 110 ,it might cause materials blocking in barrel zone;if use moisture analysis meter,the temperture setting should be on 105 .			



R							
4	16 170	170-190	180-210	180-210	180-200	180-190	50-70

1.Dawnprene TPE PVC

Dawnprene TPE is incompatible with PVC materials,hence must clean the equipment before using.

2. 120 100 2 , .

Above testing data is tested by injection sample block, cutting by the sheet size is 120 100 2 .

3. .

The properties is typical performance,is not regarding as technical index or agreement.

4.

Any reprocessing must follow the above instructions,and ensure no content impurity.

5.

Above instructions for reference only,different equipment might have difference parameters,please adjust accordingly with different mold and product shape.

SHANDONG DAWN POLYMER CO.,LTD

: . 265703

Address:Zhenxing Road,Longgang Economic Zone,Longkou,Shandong, China. 265703

() 0086-535-8868588;()0086-535-8833988

Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988