

Dawnflex TPU DN-2095-T2

	25kg/						
	1.22	g/cm ³	ASTM D792				
	95 2	A	ASTM D2240				
	45	MPa	ASTM D412				
100%	11	MPa	ASTM D412				
300%	20	MPa	ASTM D412				
	450	%	ASTM D412				
	145	KN/m	ASTM D624				
0.05%							
100							
100							
	/		/h				
	90-100		2-4				
	225-235		205-215				
	220-230		200-210				
	215-220		195-205				
	210-215		190-200				
SDS							
1. 2.							
: . 265703							
() 0086-535-8868588;()0086-535-8833988							

Dawnflex TPU DN-2095-T2

General information			
Material Properties	High transparency, low risk of precipitation, fast molding, and high strength		
Application Market	Overmolding, modification, electronic injection molding, cable		
Appearance Shape	Transparent particles		
Packing Specifications	25 kg/bag		
Processing Method	Injection Extrusion		
Physical property parameters	Typical value	Unit	Method
Density	1.22	g/cm ³	ASTM D792
Shore Hardness	95 2	A	ASTM D2240
Tensile Strength	45	MPa	ASTM D412
100% Modulus	11	MPa	ASTM D412
300% Modulus	20	MPa	ASTM D412
Elongation at Break	450	%	ASTM D412
Tear Strength	145	KN/m	ASTM D624
Processing suggestions			
Processing conditions Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%, suggesting drying as follow process:			
Drying conditions	Drying temperature/		Drying time/h
	90-100		2-4
Processing temperature			
Injection	Set Value	Extrusion	Set Value
Nozzle ()	225-235	Nozzle ()	205-215
Front Barrel ()	220-230	Front Barrel ()	200-210
Middle Barrel ()	215-220	Middle Barrel ()	195-205
Rear Barrel ()	210-215	Rear Barrel ()	190-200
Healthy Safety Environmental: Take SDS for reference			
Extra information 1.The above properties are typical performance which is not regarding as technical index or agreement. 2.Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.			
SHANDONG DAWN POLYMER Co., Ltd. Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703 Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988			