

Dawnflex TPU DN-3595-T1

	25kg/		
	1.21	g/cm ³	ASTM D792
	95 ± 2	A	ASTM D2240
	45	MPa	ASTM D412
100%	15	MPa	ASTM D412
300%	25	MPa	ASTM D412
	550	%	ASTM D412
	160	KN/m	ASTM D624
100 100	0.05%		
	/	/h	
	90-100	2-4	
	220-230		190-200
	215-220		190-200
	210-215		185-195
	210-215		180-190
SDS			
1. 2.			
: . 265703 () 0086-535-8868588;()0086-535-8833988			

Dawnflex TPU DN-3595-T1

General information			
Material Properties	High transparency, low precipitation risk, easy to post-processing, high strength.		
Application Market	Shoes, pipes, modified, cables		
Appearance Shape	Transparent particles		
Packing Specifications	25 kg/bag		
Processing Method	Injection Extrusion		
Physical property parameters	Typical value	Unit	Method
Density	1.21	g/cm ³	ASTM D792
Shore Hardness	95 ± 2	A	ASTM D2240
Tensile Strength	45	MPa	ASTM D412
100% Modulus	15	MPa	ASTM D412
300% Modulus	25	MPa	ASTM D412
Elongation at Break	550	%	ASTM D412
Tear Strength	160	KN/m	ASTM D624
Processing suggestions			
Processing conditions Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%, suggesting drying as follow process:			
Drying conditions	Drying temperature/		Drying time/h
	90-100		2-4
Processing temperature			
Injection	Set Value	Extrusion	Set Value
Nozzle ()	210-220	Nozzle ()	190-200
Front Barrel ()	205-215	Front Barrel ()	190-200
Middle Barrel ()	205-215	Middle Barrel ()	185-195
Rear Barrel ()	200-210	Rear Barrel ()	180-190
Healthy Safety Environmental: Take SDS for reference			
Extra information 1.The above properties are typical performance which is not regarding as technical index or agreement. 2.Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.			
SHANDONG DAWN POLYMER CO., Ltd. Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703 Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988			