

Dawnflex TPU DN-2595-T1

25kg/			
1.22		g/cm ³	ASTM D792
95 2		A	ASTM D2240
40		MPa	ASTM D412
100%	12	MPa	ASTM D412
300%	20	MPa	ASTM D412
500		%	ASTM D412
140		KN/m	ASTM D624
0.05%			
100			
100			
		/	/h
		90-100	2-4
220-230			190-200
215-220			190-200
210-215			185-195
210-215			180-190
SDS			
1.	中	中	
2.			
: . 265703			
() 0086-535-8868588;(典) 0086-535-8833988			

Dawnflex TPU DN-2595-T1

General information			
Material Properties	High transparency, low precipitation risk, easy to post-processing		
Application Market	Shoes, pipes, modified, cables		
Appearance Shape	Transparent particles		
Packing Specifications	25 kg/bag		
Processing Method	Injection Extrusion		
Physical property parameters	Typical value	Unit	Method
Density	1.22	g/cm ³	ASTM D792
Shore Hardness	95 2	A	ASTM D2240
Tensile Strength	40	MPa	ASTM D412
100% Modulus	12	MPa	ASTM D412
300% Modulus	20	MPa	ASTM D412
Elongation at Break	500	%	ASTM D412
Tear Strength	140	KN/m	ASTM D624
Processing suggestions			
Processing conditions			
Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%, suggesting drying as follow process:			
Drying conditions	Drying temperature/		Drying time/h
	90-100		2-4
Processing temperature			
Injection	Set Value	Extrusion	Set Value
Nozzle ()	210-220	Nozzle ()	190-200
Front Barrel ()	205-215	Front Barrel ()	190-200
Middle Barrel ()	205-215	Middle Barrel ()	185-195
Rear Barrel ()	200-210	Rear Barrel ()	180-190
Healthy & Safety & Environmental: Take SDS for reference			
Extra information			
1.The above properties are typical performance which is not regarding as technical index or agreement.			
2.Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.			
SHANDONG DAWN POLYMER CO., Ltd.			
Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703			
Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988			