



Dawnflex TPU DN-1095-T3

Dawnflex TPU DN-1095-T3

General information			
Material Properties	Good formability, high transparency, low precipitation risk, easy to post-processing		
Application Market	Electronic protection cover, shoes, pipes, casters, modified, cables		
Appearance Shape	Transparent particles		
Packing Specifications	25 kg/bag		
Processing Method	Injection Extrusion		
Physical property parameters	Typical value	Unit	Method
Density	1.22	g/cm ³	ASTM D792
Shore Hardness	95 1	A	ASTM D2240
Tensile Strength	35	MPa	ASTM D412
100% Modulus	8	MPa	ASTM D412
300% Modulus	14	MPa	ASTM D412
Elongation at Break	550	%	ASTM D412
Tear Strength	120	KN/m	ASTM D624
Processing suggestions			
Processing conditions Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%, suggesting drying as follow process:			
Drying conditions	Drying temperature/		Drying time/h
	90-100		2-4
Processing temperature			
Injection	Set Value	Extrusion	Set Value
Nozzle ()	215-225	Nozzle ()	200-210
Front Barrel ()	210-220	Front Barrel ()	195-205
Middle Barrel ()	210-220	Middle Barrel ()	190-200
Rear Barrel ()	205-215	Rear Barrel ()	190-200
Healthy Safety Environmental: Take SDS for reference			
Extra information 1.The above properties are typical performance which is not regarding as technical index or agreement. 2.Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.			
SHANDONG DAWN POLYMER Co., Ltd. Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703 Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988			