

## 聚乙烯熔喷专用料 Z-1800H

### 产品说明书/Technical Data Sheet

|            |     |      |
|------------|-----|------|
| /Attribute | 120 | 500H |
|------------|-----|------|

|               |
|---------------|
| /Applications |
|---------------|

| Properties                    | Test Method    | Test Condition | Unit    | Typical Values | Technical Specification |
|-------------------------------|----------------|----------------|---------|----------------|-------------------------|
| Melt Flow Rate                | GB/T 3682      | 230 2.16kg     | g/10min | 1800           | 1800 100                |
| ASH                           | GB/T9345.1     | 850 50         | %       | 0.025          | 0.03                    |
| Melting Point                 | GB/T19466.3    | 20mm/min       |         | 164.8          | 163                     |
| Molecular weight distribution | ISO16014-4 GPC | 150 1ml/min    | /       | 3.1            | 2-4                     |
| Volatile constituents         | GB/T 2914      | 110 2          | %       | 0.15           | 0.2                     |

Values shown are based on testing of injection moulded laboratory test specimens. Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Please note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions and coloring. Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions. Each user is responsible for making its own

appropriate end-use testing and analysis. This information and our technical advice-whether verbal, in writing or by the way of trial are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved./